

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (currently amended): A multi-piece solid golf ball comprising a solid core, a mantle of at least one layer, and a cover, wherein

the solid core is made of a rubber composition comprising (A) 100 parts by weight of a base rubber that contains 60 to 100 wt% of a polybutadiene of at least 60% cis-1,4 structure and synthesized using a rare-earth catalyst, (B) 0.1 to 0.8 part by weight of an organic peroxide, (C) an unsaturated carboxylic acid or an unsaturated carboxylic acid metal salt or both, (D) an organic sulfur compound selected from the group consisting of thiophenols, thionaphthols, halogenated thiophenols, and metal salts thereof, and (E) an inorganic filler, has a deflection when subjected to a load of 980 N (100 kgf) of 3.5 to 6.5 mm, and has a diameter of 30 to 40 mm;

the mantle of at least one layer is made of a thermoplastic resin composition, has a thickness per layer of 0.5 to 2.0 mm, and includes an outermost layer which is in contact with the cover and has a Shore D hardness of 20 to 60;

the cover is made primarily of a mixture of (F) 100 parts by weight of a resin composition containing an ionomer resin and (G) 5 to 40 parts by weight of an inorganic filler, has a thickness of 0.5 to 2.5 mm and a Shore D hardness of 50 to 70, and satisfies the condition (Shore D hardness of mantle outermost layer)  $\leq$  (Shore D hardness of cover); and

the golf ball has a deflection when subjected to a load of 980 N (100 kgf) of 3.0 to 5.5 mm.

2. (original): The golf ball of claim 1, wherein the polybutadiene is a modified polybutadiene prepared by synthesis using a neodymium catalyst, followed by reaction with a terminal modifier.

3. (currently amended): The golf ball of claim 1, wherein the rubber composition comprises:

(A) 100 parts by weight of a base rubber containing 60 to 100 wt% of a polybutadiene of at least 60% cis-1,4 structure and synthesized using a rare-earth catalyst,

(B) at least two kinds of organic peroxide,

(C) 10 to 60 parts by weight of an unsaturated carboxylic acid or an unsaturated carboxylic acid metal salt or both,

(D) 0.1 to 5 parts by weight of ~~an~~ the organic sulfur compound, and

(E) 5 to 80 parts by weight of an inorganic filler.

4. (original): The golf ball of claim 1, wherein the thermoplastic resin composition of which the mantle is made comprises:

100 parts by weight of resin components which include a base resin of (P) an olefin/unsaturated carboxylic acid binary random copolymer or a metal ion neutralization product of an olefin/unsaturated carboxylic acid binary random copolymer or both in admixture with (Q) an olefin/unsaturated carboxylic acid/unsaturated carboxylic acid ester ternary random copolymer or a metal ion neutralization product of an olefin/unsaturated carboxylic acid/unsaturated carboxylic acid ester ternary random copolymer or both in a weight ratio P/Q of 100:0 to 25:75, and (R) a non-ionomeric thermoplastic elastomer in a weight ratio (P+Q)/R of 100:0 to 50:50;

(S) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of 280 to 1,500, or both; and

(T) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing un-neutralized acid groups in the base resin and component S.

5. (original): The golf ball of claim 1, wherein the mantle consists of an inner layer and an outer layer.

6. (original): The golf ball of claim 1, wherein component F, the resin composition containing an ionomer resin is composed primarily of a mixture of (M) an amino-terminated block polymer and (N) an ionomer resin in a weight ratio  $M/N$  of 3/97 to 60/40.

7. (original): The golf ball of claim 1, wherein the cover is composed primarily of a mixture of (F) 100 parts by weight of a resin composition containing an ionomer resin and (G) 5 to 30 parts by weight of barium sulfate.

8. (original): The golf ball of claim 1, wherein the cover bears on a surface thereof a plurality of dimples, each dimple having a spatial volume below a planar surface circumscribed by an edge of the dimple and having a surface area circumscribed by the dimple edge on a hypothetical sphere represented by the surface of the golf ball cover were it to have no dimples; which golf ball has a dimple volume occupancy  $VR$ , defined as the ratio of the sum of the individual dimple volumes to the volume of the hypothetical sphere, of 0.70 to 1.00%, and a dimple surface coverage  $SR$ , defined as the ratio of the sum of the individual dimple surface areas to the surface area of the hypothetical sphere, of 70 to 85%.

9. (original): The golf ball of claim 1, having a weight of 45.0 to 45.93 g.

10. (new): A multi-piece solid golf ball comprising a solid core, a mantle of at least one layer, and a cover, wherein

AMENDMENT

U.S. Appln. No. 10/720,522

the solid core is made of a rubber composition comprising (A) 100 parts by weight of a base rubber that contains 60 to 100 wt% of a polybutadiene of at least 60% cis-1,4 structure and synthesized using a rare-earth catalyst, (B) 0.1 to 0.8 part by weight of at least two kinds of an organic peroxide, (C) 10 to 60 parts by weight of an unsaturated carboxylic acid or an unsaturated carboxylic acid metal salt or both, (D) 0.1 to 5 parts by weight of an organic sulfur compound and (E) 5 to 80 parts by weight of an inorganic filler, has a deflection when subjected to a load of 980 N (100 kgf) of 3.5 to 6.5 mm, and has a diameter of 30 to 40 mm;

the mantle of at least one layer is made of a thermoplastic resin composition, has a thickness per layer of 0.5 to 2.0 mm, and includes an outermost layer which is in contact with the cover and has a Shore D hardness of 20 to 60;

the cover is made primarily of a mixture of (F) 100 parts by weight of a resin composition containing an ionomer resin and (G) 5 to 40 parts by weight of an inorganic filler, has a thickness of 0.5 to 2.5 mm and a Shore D hardness of 50 to 70, and satisfies the condition (Shore D hardness of mantle outermost layer)  $\leq$  (Shore D hardness of cover); and

the golf ball has a deflection when subjected to a load of 980 N (100 kgf) of 3.0 to 5.5 mm.

11. (new): A multi-piece solid golf ball comprising a solid core, a mantle of at least one layer, and a cover, wherein

the solid core is made of a rubber composition comprising (A) 100 parts by weight of a base rubber that contains 60 to 100 wt% of a polybutadiene of at least 60% cis-1,4 structure and synthesized using a rare-earth catalyst, (B) 0.1 to 0.8 part by weight of an organic peroxide, (C) an unsaturated carboxylic acid or an unsaturated carboxylic acid metal salt or both, (D) an organic sulfur compound and (E) an inorganic filler, has a deflection when subjected to a load of 980 N (100 kgf) of 3.5 to 6.5 mm, and has a diameter of 30 to 40 mm;

AMENDMENT

U.S. Appln. No. 10/720,522

the mantle of at least one layer is made of a thermoplastic resin composition, has a thickness per layer of 0.5 to 2.0 mm, and includes an outermost layer which is in contact with the cover and has a Shore D hardness of 20 to 60;

the cover is made primarily of a mixture of (F) 100 parts by weight of a resin composition containing an ionomer resin and (G) 5 to 40 parts by weight of an inorganic filler, has a thickness of 0.5 to 2.5 mm and a Shore D hardness of 50 to 70, and satisfies the condition  $(\text{Shore D hardness of mantle outermost layer}) \leq (\text{Shore D hardness of cover})$ ; and

the golf ball has a deflection when subjected to a load of 980 N (100 kgf) of 3.0 to 5.5 mm,

wherein the thermoplastic resin composition of which the mantle is made comprises:

100 parts by weight of resin components which include a base resin of (P) an olefin/unsaturated carboxylic acid binary random copolymer or a metal ion neutralization product of an olefin/unsaturated carboxylic acid binary random copolymer or both in admixture with (Q) an olefin/unsaturated carboxylic acid/unsaturated carboxylic acid ester ternary random copolymer or a metal ion neutralization product of an olefin/unsaturated carboxylic acid/unsaturated carboxylic acid ester ternary random copolymer or both in a weight ratio P/Q of 100:0 to 25:75, and (R) a non-ionomeric thermoplastic elastomer in a weight ratio (P+Q)/R of 100:0 to 50:50;

(S) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of 280 to 1,500, or both; and

(T) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing un-neutralized acid groups in the base resin and component S.

12. (new): A multi-piece solid golf ball comprising a solid core, a mantle of at least one layer, and a cover, wherein

## AMENDMENT

U.S. Appln. No. 10/720,522

the solid core is made of a rubber composition comprising (A) 100 parts by weight of a base rubber that contains 60 to 100 wt% of a polybutadiene of at least 60% cis-1,4 structure and synthesized using a rare-earth catalyst, (B) 0.1 to 0.8 part by weight of an organic peroxide, (C) an unsaturated carboxylic acid or an unsaturated carboxylic acid metal salt or both, (D) an organic sulfur compound and (E) an inorganic filler, has a deflection when subjected to a load of 980 N (100 kgf) of 3.5 to 6.5 mm, and has a diameter of 30 to 40 mm;

the mantle of at least one layer is made of a thermoplastic resin composition, has a thickness per layer of 0.5 to 2.0 mm, and includes an outermost layer which is in contact with the cover and has a Shore D hardness of 20 to 60;

the cover is made primarily of a mixture of (F) 100 parts by weight of a resin composition containing an ionomer resin and (G) 5 to 40 parts by weight of an inorganic filler, has a thickness of 0.5 to 2.5 mm and a Shore D hardness of 50 to 70, and satisfies the condition (Shore D hardness of mantle outermost layer)  $\leq$  (Shore D hardness of cover); and

the golf ball has a deflection when subjected to a load of 980 N (100 kgf) of 3.0 to 5.5 mm,

wherein component F, the resin composition containing an ionomer resin is composed primarily of a mixture of (M) an amino-terminated block polymer and (N) an ionomer resin in a weight ratio M/N of 3/97 to 60/40.

13. (new): A multi-piece solid golf ball comprising a solid core, a mantle of at least one layer, and a cover, wherein

the solid core is made of a rubber composition comprising (A) 100 parts by weight of a base rubber that contains 60 to 100 wt% of a polybutadiene of at least 60% cis-1,4 structure and synthesized using a rare-earth catalyst, (B) 0.1 to 0.8 part by weight of an organic peroxide, (C) an unsaturated carboxylic acid or an unsaturated carboxylic acid metal salt or both, (D) an organic sulfur compound and (E) an inorganic filler, has a deflection when subjected to a load of 980 N (100 kgf) of 3.5 to 6.5 mm, and has a diameter of 30 to 40 mm;

the mantle of at least one layer is made of a thermoplastic resin composition, has a thickness per layer of 0.5 to 2.0 mm, and includes an outermost layer which is in contact with the cover and has a Shore D hardness of 20 to 60;

the cover is made primarily of a mixture of (F) 100 parts by weight of a resin composition containing an ionomer resin and (G) 5 to 40 parts by weight of an inorganic filler, has a thickness of 0.5 to 2.5 mm and a Shore D hardness of 50 to 70, and satisfies the condition  $(\text{Shore D hardness of mantle outermost layer}) \leq (\text{Shore D hardness of cover})$ ; and

the golf ball has a deflection when subjected to a load of 980 N (100 kgf) of 3.0 to 5.5 mm,

wherein the cover bears on a surface thereof a plurality of dimples, each dimple having a spatial volume below a planar surface circumscribed by an edge of the dimple and having a surface area circumscribed by the dimple edge on a hypothetical sphere represented by the surface of the golf ball cover were it to have no dimples; which golf ball has a dimple volume occupancy VR, defined as the ratio of the sum of the individual dimple volumes to the volume of the hypothetical sphere, of 0.70 to 1.00%, and a dimple surface coverage SR, defined as the ratio of the sum of the individual dimple surface areas to the surface area of the hypothetical sphere, of 70 to 85%.

14. (new): The multi-piece solid golf ball of claim 1, wherein the organic sulfur compound is selected from the group consisting of pentachlorothiophenol; pentafluorothiophenol; pentabromothiophenol; p-chlorothiophenol; zinc salts of pentachlorothiophenol, pentafluorothiophenol, pentabromothiophenol, or p-chlorothiophenol; diphenylpolysulfides; dibenzylpolysulfides; dibenzoylpolysulfides; dibenzothiazoylpolysulfides; dithiobenzoylpolysulfides having 2 to 4 sulfurs; alkylphenyldisulfides; furan ring-bearing sulfur compounds; and thiophene ring-bearing sulfur compounds.

15. (new): The multi-piece solid golf ball of claim 1, wherein the organic sulfur compound is diphenyldisulfide and/or a zinc salt of pentachlorothiophenol.

AMENDMENT

U.S. Appln. No. 10/720,522

16. (new): The multi-piece solid golf ball of claim 1, wherein a second polybutadiene other than said polybutadiene is added and the second polybutadiene is synthesized by using a Group VIII catalyst and has a Mooney viscosity of less than 50.